PATENT APPLICATION

RESPONSE UNDER 37 CFR §1.116 EXPEDITED PROCEDURE TECHNOLOGY CENTER ART UNIT

In re the Application of

Shinji SHIMIZU et al.

Application No.: 09/242,828

Filed: February 24, 1999

EASILY ADHESIVE POLYAMIDE FILM

Group Art Unit: 1773

Examiner:

D. Nakarani

Docket No.:

102761

AMENDMENT AFTER FINAL REJECTION UNDER 37 CFR §1.146

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Director of the U.S. Patent and Trademark Office Washington, D.C. 20231

Sir:

For:

In reply to the Office Action mailed January 12, 2001, please amend the aboveidentified application as follows:

IN THE SPECIFICATION:

Page 5, lines 22-29, delete current paragraph and insert therefor:

The present invention adds acetylene glycol, in which each carbon atom immediately adjacent to a triple-bonded carbon atom is substituted with a hydroxyl group and methyl group, and/or a non-ionic surface active agent, which is an addition product of the ethylene oxide, to the water polyurethane resin. For the surface active agent Surfynol 104 and 140, produced by Nissan Chemical Industries, are recommended. Adding ratio between 0.01% and 1.0% to the solid content of the water polyurethane resin is desirable.